



9080 - High Performance Non-woven Double Coated Tape

Product Data Sheet

Supersedes: New

Product Description 9080 is a double coated acrylic adhesive on a non-woven tissue carrier. It has a very high level of initial tack and good adhesion to a wide variety of surfaces including LSE materials.

Physical Properties
Not for specification purposes

Adhesive Type	Acrylic	
Carrier	Non-woven tissue	
Thickness (ASTM D-3652) Tape Liner Total	0.160 mm (160µm) 0.160 mm (160 µm) 0.320 mm (320µm)	
Release Liner	White polycoated paper with 3M logo	
Tape Colour	White	
Shelf Life	12 months from date of despatch by 3M when stored in the original carton at 21°C (70°F) & 50 % Relative Humidity	

Performance Characteristics
Not for specification purposes

Adhesion to Stainless Steel ASTM D 3330	7.5 N/cm	
Static Shear Resistance ASTMD 3654	500g , 6.4cm ² gives 10,000 min+; @ R.T.	
Temperature Performance Max : Minutes / Hours Max : Days / Weeks Minimum	120°C 90°C -30°C	
Solvent Resistance	Good	

Date : New
9080 High Performance Non-
woven Double Coated Tape

Application Techniques

1. Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure develops better adhesive contact & thus improves bond strength.

2. To obtain optimum adhesion, the bonding surfaces must be clean dry and well unified. A typical surface cleaning solvent is isopropyl alcohol & water. Use proper safety precautions for handling solvents.

3. Ideal tape application temperature range is 21°C to 38°C (70°F to 100°F). Initial tape application to surfaces at temperatures below 10°C (50°F) is not recommended because the adhesive becomes too firm to adhere readily. However once properly applied low temperature holding is generally satisfactory.

Applications

9080 is well suited to bonding together a wide variety of similar and dissimilar materials such as wood, metals, glass, papers, paints, and many plastics and fabrics.

It shows a high level of adhesion to LSE materials such as Polypropylene and some Polyethylenes as well as coated papers and varnishes.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.



Tapes & Adhesives

© 3M United Kingdom PLC 1996

3M United Kingdom PLC
3M House,
28 Great Jackson Street,
Manchester,
M15 4PA

Product Information :
Tel 0870 60 800 50
Fax 0870 60 700 99

3M Ireland
3M House, Adelphi Centre,
Upper Georges Street,
Dun Laoghaire, Co. Dublin,
Ireland

Customer Service :
Tel (01) 280 3555
Fax (01) 280 3509